

150# NEOPRENE FULL FACE GASKETS

Features

Neoprene (Chloroprene Rubber) has excellent resistance to oils, ozone, sunlight and aging with low permeability to gases. It is recommended for use with gasoline and non-aromatic solvents. Neoprene gaskets offer little resistance to and should not be used in strong oxidants, and aromatic and chlorate hydrocarbons.

Standards

• Meets ASME B16.21 for 150# gaskets

• Dimensions: ASME B16.5

Service Limits

Max. Temperature: 170°F (77°C)
Min. Temperature: -20°F (-29°C)




Typical Physical Properties

71 - 7 - 1 - 1 - 1	
Property	Value
Durometer Hardness	65 Shore A ±5
Tensile	500 PSI
Elongation	300%
Density	93~100 lbs/ft ³
Compressibility	20~30%
Finish	Smooth
Color	Black

Properties and application parameters shown on this data sheet are typical. Failure to select proper sealing products could result in property damage and/or serious personal injury.

Figure Number Matrix



DOC: FNWNE13 Ver. 7/2013

© 2013 - FNW. All rights reserved.

The FNW logo is a trademark of Ferguson Enterprises, Inc., PL Sourcing, PO Box 2778, Newport News, VA 23609

www.fnw.com