

Product Data Sheet

GTF-320

Thrace-LINQ® GTF-320 is woven in a stable weave pattern; using high-tenacity polypropylene yarns. This geotextile has been UV stabilized and is resistant to commonly encountered chemicals, mildew, and insects, found in soil.

PROPERTY	TEST PROCEDURE	METRIC		ENGLISH	
		MARV		MARV	
Grab Tensile Strength	ASTM-D4632	1779 / 1557	N	400 / 350	lbs
Grab Tensile Elongation	ASTM-D4632	15 / 6	%	15 / 6	%
Wide Width Tensile ULT	ASTM-D4595	39 / 39	kN/m	2700 / 2640	lbs/ft
Wide Width Elongation	ASTM-D4595	9.0 / 8.0	%	9.0 / 8.0	%
Trapezoid Tear	ASTM-D4533	738 / 645	N	166 / 145	lbs
CBR Puncture	ASTM-D6241	6561	N	1475	lbs
Permittivity	ASTM-D4491	0.7	sec ⁻¹	0.7	sec ⁻¹
WaterFlow Rate	ASTM-D4491	2037	l/min/m ²	50	gpm/ft ²
Apparent Opening Size (AOS)	ASTM-D4751	0.425	mm	40	USSieve
UV Stability @ 500 hrs	ASTM-D4355	80	%	80	%

- Notes:**
- Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics.
 - Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241.

PACKAGING		METRIC				ENGLISH			
		Area	Width	Length	Est. Weight	Area	Width	Length	Est. Weight
		m2	m	m	kg	yd2	ft	ft	lbs
Roll Sizes		418	4.6	91.4	127	500	15	300	279

*Physical properties reflect industry standards. Roll Data may reflect higher values than those listed above.
Roll lengths and widths have a tolerance of +/- 1%.*

The property values listed above are effective 09/2012 and are subject to change without notice.

This information relates to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date manufactured. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself or herself as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information, nor do we offer any warranty against infringement.

LINQ and the Thrace-LINQ emblem are registered trademarks of Thrace-LINQ, Inc.