

# Mirafi<sup>®</sup> 140NC



Mirafi<sup>®</sup> 140NC is a needlepunched nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Mirafi<sup>®</sup> 140NC is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas is accredited by a2La (The American Association for Laboratory Accreditation) and Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). NTPEP Number: GTX-2012-01-045

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	100 (445)	100 (445)
Grab Tensile Elongation	ASTM D4632	%	60	60
Toughness	Grab Tensile Strength x Elongation	lbs	6000	
Trapezoid Tear Strength	ASTM D4533	lbs (N)	45 (200)	45 (200)
CBR Puncture Strength	ASTM D6241	lbs (N)	250 (1113)	
Apparent Opening Size (AOS) <sup>1</sup>	ASTM D4751	U.S. Sieve (mm)	70 (0.212)	
Permittivity	ASTM D4491	sec <sup>-1</sup>	2.0	
Flow Rate	ASTM D4491	gal/min/ft <sup>2</sup> (l/min/m <sup>2</sup> )	140 (5704)	
Mass / Unit Area	ASTM D5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	4.0 (136)	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70	

<sup>1</sup> ASTM D4751: AOS is a Maximum Opening Diameter Value

Physical Properties	Unit	Typical Value	
Roll Dimensions (width x length)	ft (m)	12.5 x 360 (3.8 x 110)	15 x 360 (4.5 x 110)
Roll Area	yd <sup>2</sup> (m <sup>2</sup> )	500 (418)	600 (502)
Estimated Roll Weight	lb (kg)	139 (63)	167 (76)

© 2012 TenCate Geosynthetics Americas  
Mirafi<sup>®</sup> is a registered trademark of Nicolon Corporation

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.



365 South Holland Drive  
Pendergrass, GA 30567

Tel 706 693 2226  
Tel 888 795 0808

Fax 706 693 4400  
[www.tencate.com](http://www.tencate.com)

FGS000388  
ETQR29

